

ARTICLE

Hidden Strength of Nanostructured Metallic Materials

Aleksander Katarzyna* and Wojciech Zbigniew

Department of Analytical Chemistry and Chemical Metallurgy, Faculty of Chemistry, Wrocław University of Science and Technology, 50-370 Wrocław, Poland

*Corresponding author: aleks.kat.91@pwr.edu.pl

(Received: 05 July 2024; Revised: 19 November 2024; Accepted: 03 January 2025; Published: 12 January 2025)

Abstract

Metallic materials engineered at the nanoscale demonstrate strength levels up to three times higher compared to traditional commercial crystalline alloys. This remarkable enhancement stems from recent advancements in nanostructure design strategies, which have revolutionized how we approach material engineering. Due to their unique characteristics, nanomaterials exhibit exceptional chemical reactivity and mechanical properties that their conventional counterparts simply cannot match. These advantages arise from carefully controlled grain sizes and the development of heterogeneous nanostructures in both crystalline and non-crystalline metallic materials. Furthermore, innovative approaches like supra-nano-dual-phase (SNDP) nanostructures combine supra-nano sized crystals with metallic glasses, creating materials with unprecedented performance capabilities. In this article, we will explore why nanostructured metallic materials consistently outperform traditional alloys, examine their manufacturing processes, and investigate their real-world applications across various industries. We will also analyze the cost-effectiveness and future potential of these advanced materials in engineering applications.

Keywords: Ductility enhancement; Grain boundaries; Nanostructuring; Strength optimization; Thermal stability

Abbreviations: GB: Grain Boundary, GND: Geometrically Necessary Dislocations, HNT: Hierarchical Nanotwinned, NS: Nanostructured, SNDP: Supra-Nano-Dual-Phase

1. Core Types of Nanostructured Metallic Materials

The semiconductor industry has reached a critical milestone with the 3nm process node, marking a significant advancement in chip manufacturing capabilities. The 3nm node represents precise specifications, including a gate length of 16-18nm and a metal pitch of 30nm [1, 2, 3, 4, 5].

Nanostructured metallic materials exhibit extraordinary physicochemical properties primarily because of their unique structural arrangements at the nanoscale. These materials demonstrate significantly enhanced performance compared to their bulk counterparts, particularly in terms of mechanical strength and reactivity.

1.1 Surface Area to Volume Ratio Benefits

The reduction of bulk materials to nanometer scale dramatically increases their surface-to-volume ratio, consequently affecting their chemical reactivity and surface-dependent properties. When materials are divided into smaller fragments, the total surface area increases exponentially - for instance, reducing a material's size can increase its surface area by a factor of up to 109. This enhanced surface area drives chemical, electrical, and biological interactions, while the volume influences weight,

cost, and momentum-related properties (Fig. 1) [6].




Figure 1. Bimodal nanostructure Cu

1.2 Size Effects on Material Properties

The size-dependent characteristics of nanostructured materials become particularly evident when dimensions fall below 100 nanometers. These size effects significantly influence. Nanotwinned (NT) structures represent a significant advancement in nanostructured metallic materials. These structures contain twin boundaries that act as coherent interfaces, substantially improving mechanical and physical properties. Notably, hierarchical nanotwinned (HNT) structures, featuring multiorientation nanotwins, create complex spatial multidimensional arrangements that effectively hinder dislocation movement [7, 8].

1.3 Grain-Refined Materials

Grain refinement into the nanoscale significantly strengthens metallic materials through the classical Hall-Petch relation. Nevertheless, introducing high-density grain boundaries creates a substantial driving force for migration, potentially leading to grain coarsening under mechanical loading or at temperatures below typical recrystallization points. Scientists have developed several strategies to stabilize these refined structures, including solute drag, second phase drag, and chemical ordering. Metal Matrix Nanocomposites (MMNCs) offer distinct advantages over traditional composites, particularly in terms of high-temperature stability, strength, and wear resistance. These materials can be synthesized through various methods [9]:

1. Deformation processing utilizing high strain rates
2. Vapor phase processing for thin film deposition
3. Solidification processing for bulk production

MMNCs have demonstrated remarkable improvements in specific material properties with minimal reinforcement additions. For example, incorporating just one volume percentage of nanosize ceramics has produced greater strength increases in aluminum and magnesium composites than higher loading levels of micron-sized additions. Moreover, these nanocomposites exhibit enhanced thermal stability when thermodynamic and kinetic strategies are effectively combined [10].

2. How Nanostructuring Changes Metal Properties

Abstract: This section examines the fundamental changes in metallic properties through nanostructuring, focusing on strength-ductility relationships, strain hardening mechanisms, and thermal stability characteristics. We analyze how various nanostructuring approaches modify material behavior and performance under different conditions (Fig. 2) [11].




Figure 2. Application areas of nanotechnology

The manipulation of metallic materials at nanoscale creates extraordinary property modifications that surpass conventional engineering limits. Through careful control of structural features, scientists have discovered methods to overcome traditional material constraints.

2.1 Strength Improvements

The relationship between grain size and material strength follows the Hall-Petch effect until grain dimensions reach approximately 20 nanometers. Beyond this point, an inverse relationship emerges where further size reduction actually decreases yield strength. This phenomenon occurs since extremely small grains cannot support dislocation pile-up, shifting the dominant deformation mechanism to grain boundary sliding [12, 13].

2.2 Ductility Enhancement

Traditionally, increasing material strength resulted in decreased ductility. However, recent advances in nanostructuring have created pathways to overcome this limitation. The introduction of bimodal structures, incorporating both nano-scale and micron-level grains, produces materials with exceptional strength-ductility combinations.

The incorporation of nanotwinned structures substantially improves mechanical properties through coherent twin boundaries. Similarly, gradient nanostructures, where grain sizes progressively change from nano to micro scale, demonstrate remarkable performance advantages [14].

2.3 Thermal Stability

Thermal stability represents a crucial characteristic for nanostructured metals, especially during extended operation at elevated temperatures. The large volume fraction of grain boundaries in nanostructured materials creates unique challenges for maintaining structural integrity.

Two primary approaches address thermal stability:

1. Thermodynamic Stabilization:

- Reduces grain boundary energy through solute segregation
 - Commonly implemented in Ni-W and Ni-Fe alloys
 - Creates resistance to grain coarsening
2. Kinetic Stabilization:
- Employs solute dragging and second phase pinning
 - Counteracts driving forces for grain growth
 - Achieves higher temperature stability than thermodynamic methods

The effectiveness of these stabilization strategies becomes particularly evident during long-term exposure to elevated temperatures. Kinetic approaches have demonstrated superior results in maintaining nanostructured features at higher temperatures.

Recovery processes in nanostructured metals exhibit distinct behavior compared to conventional materials. Initially, static recovery strengthens nanostructured metals, contrary to its softening effect in coarse-grained materials. Additionally, dynamic recovery during deformation can enhance strain-hardening capabilities, leading to improved uniform elongation (Fig. 3) [15].




Figure 3. A new perspective on pore growth in anodic alumina films

The supra-nano-dual-phase (SNDP) structure represents an advanced approach to property enhancement. This configuration combines two phases with different structures or compositions, resulting in superior mechanical properties alongside enhanced functional characteristics such as magnetic properties and thermal stability [16].

Recent experimental findings indicate that strain partitioning between different structural regions generates geometrically necessary dislocations (GNDs), contributing significantly to work hardening. This mechanism proves particularly effective in bimodal structures, where the interaction between coarse and fine grains creates multidirectional stress states and strain gradients. Through careful control of these nanostructuring approaches, researchers have achieved remarkable combinations of strength and ductility. The key lies in creating heterogeneous structures that maintain high strength while providing sufficient strain hardening capacity to prevent premature failure [17].

3. Manufacturing Methods for Nanostructured Metals

This section delves into two primary manufacturing techniques for nanostructured metals: mechanical alloying and severe plastic deformation. We examine process parameters, equipment specifications, and resulting material characteristics that make these methods effective for producing advanced metallic materials. Manufacturing nanostructured metallic materials requires precise control over processing conditions alongside sophisticated equipment. These advanced manufacturing methods create materials with exceptional properties through careful manipulation of microstructure at the nanoscale.

3.1 Mechanical Alloying Process

Mechanical alloying, developed in 1966, represents a sophisticated powder processing technique that produces nanostructured materials through repeated cold welding, fracturing, and rewelding of powder particles. The process maintains a ball-to-powder weight ratio of 10:1 or higher, enabling efficient material processing (Fig. 4) [18].




Figure 4. Nanoarchitected materials

Modern mechanical alloying facilities demonstrate remarkable production capabilities. Russian facilities currently produce 40-50 kg of powder within 24-48 hours, whereas high-speed mills achieve outputs reaching 5,000 kg per hour. Throughout processing, powder particles undergo severe plastic deformation, increasing their surface-to-volume ratio alongside rupturing surface contamination films.

The technique proves particularly effective in creating unique material combinations. When processing ductile-ductile powder mixtures, layered composite particles form through cold welding. Alternatively, brittle-brittle combinations undergo repeated fracturing, leading to refined particle sizes. The steady-state condition ultimately yields homogenized microstructures with compositions matching initial powder proportions [19, 20].

3.2 Severe Plastic Deformation

Severe plastic deformation (SPD) stands out as the most effective method for producing bulk ultrafine-grained and nanostructured materials. This technique introduces substantial deformation without breaking or cracking the metal.

Several SPD methods have emerged as industry standards:

1. Angular channel pressing

2. High-pressure torsion
3. Multidirectional forging
4. Extrusion-cyclic compression
5. Cumulative climbing connection
6. Consecutive concreting and smoothing
7. High-pressure pipe torsion

The EQD (Eutectoid element alloying→Quenching→Hot deformation) strategy represents an innovative approach within SPD processing. This method achieves remarkable stability, with nanostructured Ti6Al4V5Cu alloy maintaining stability up to 973 K. The process proves compatible with existing industrial production lines, thereby addressing previous challenges of high-cost and low-efficiency manufacturing. Through careful control of processing parameters, SPD methods create materials with exceptional properties. The technique generates large densities of lattice defects, alongside promoting grain refinement to submicrometer or nanometer scales. These structural modifications lead to enhanced mechanical properties, including superior strength combined with high ductility.

Recent developments in SPD processing focus on scaling up sample sizes and modifying shapes for industrial applications. Over 100 SPD methods or modifications now exist, incorporating techniques like friction stir processing, hydrostatic extrusion, and KOBO extrusion. These advancements address previous limitations in sample size and shape, enabling broader commercial applications. The mechanochemical processing (MCP) variant offers a cost-effective approach for producing nanopowders. Operating at low temperatures, MCP utilizes conventional ball mills as chemical reactors. The process increases reaction kinetics through intimate mixing and refinement of grain structure to nanometer scales [21].

4. Real Performance Data from Industry Tests

Laboratory tests alongside industrial applications reveal remarkable performance improvements in nanostructured metallic materials. These advancements stem from precise control over material structure at nanoscale dimensions. Recent testing data demonstrates substantial strength enhancements through nanostructuring. The HPT alloy exhibits exceptional tensile properties, achieving an ultimate tensile strength of 966 ± 5 MPa alongside a yield strength of 924 ± 3 MPa. Upon natural aging, these values stabilize at 851 ± 6 MPa for UTS and 796 ± 5 MPa for YS as given in Table 1:

Table 1. Stable Potential Windows

Property	HPT Alloy	Naturally Aged HPT	Conventional Al-Zn-Mg-Cu
UTS (MPa)	966 ± 5	851 ± 6	450-600
YS (MPa)	924 ± 3	796 ± 5	Not Available
EL (%)	1.8 ± 0.1	6.8 ± 0.2	Higher

The naturally aged HPT alloy demonstrates balanced mechanical properties, maintaining high strength alongside improved ductility. This enhancement primarily results from grain refinement strengthening combined with precipitation strengthening mechanisms. Impact toughness evaluations reveal unique characteristics in nanostructured materials. Contrary to conventional metals, nanostructured titanium exhibits enhanced impact toughness at lower temperatures, specifically at -70°C and -196°C . This unprecedented behavior contradicts traditional observations in coarse-grained materials.

The improved low-temperature performance stems from increased strength coupled with maintained ductility. Smaller fracture dimples at lower temperatures indicate more uniform deforma-

tion processes. These characteristics make nanostructured materials particularly suitable for low-temperature applications requiring high impact resistance [22, 23].

4.1 Fatigue Life Analysis

Fatigue performance represents a critical aspect of material durability. Surface modification through nanostructuring substantially improves fatigue resistance. The fatigue limit of surface gradient nanostructured zirconium reaches approximately 204 MPa, marking a 28.3% improvement over the original sample's 159 MPa.

Fatigue damage accumulation follows distinct patterns in nanostructured materials. Cracks typically initiate along persistent slip bands on material surfaces. Surface nanocrystalline layers effectively suppress crack nucleation through:

1. Reduced strain localization
2. Enhanced surface hardness
3. Residual compressive stress
4. Work-hardened regions

The mean stress effects significantly influence fatigue behavior, primarily in high-cycle fatigue regimes. Positive mean stresses accelerate fatigue damage accumulation through increased crack opening, whereas compressive mean stresses benefit fatigue strength. Recent investigations utilizing artificial neural networks have advanced fatigue life prediction capabilities. These models assess mean stress effects on fatigue resistance, providing designers with reliable high-cycle fatigue strength data. The approach proves particularly valuable for metallic materials subjected to predominant tensile loading conditions.

Surface gradient nanostructures demonstrate remarkable fatigue performance improvements through multiple mechanisms. The high strength of nanocrystalline structures effectively prevents fatigue crack initiation. Furthermore, discontinuous growth of surface nanocrystals occurs during fatigue loading, driven by stored energy within nanocrystals. The synergistic effects of surface nanocrystals, enhanced hardness, alongside residual compressive stress create robust barriers against crack initiation. This combination prolongs crack initiation life, ultimately extending overall fatigue performance. Through careful control of these parameters, engineers can now design components with substantially improved service life under cyclic loading conditions [24].

5. Cost vs Performance Analysis

The economic viability of nanostructured metallic materials extends beyond initial production costs, encompassing their entire operational lifespan. Through careful analysis of manufacturing processes alongside performance benefits, a clearer picture emerges regarding their true value proposition.

Life cycle assessment (LCA) methodologies reveal the comprehensive environmental and economic impacts throughout a product's existence. The assessment spans raw material acquisition through manufacturing phases, ultimately determining long-term value. This systematic approach identifies material usage, energy consumption, and environmental emissions, providing crucial insights into total ownership costs as mentioned in Table 2:

The evaluation of nanomaterial products typically follows a cradle-to-gate approach, incorporating raw material extraction, transportation, and manufacturing processes. Although disposal management remains challenging without international regulations, most assessments presume similar handling to conventional products from Table 3 [25, 26]:

Traditional manufacturing methods often require substantial tooling investments, accounting for

Table 2. Stable Potential Windows

LCA Component	Assessment Parameters	Value Indicators
Raw Materials	Resource consumption, Material quality	Material efficiency ratio
Manufacturing	Energy usage, Process emissions	Production yield rate
Usage Phase	Performance benefits, Maintenance needs	Operational cost savings
End-of-Life	Disposal management, Recycling potential	Resource recovery value

Table 3. Stable Potential Windows

Cost Component	Percentage of Total Cost	Key Considerations
Equipment Investment	45-74%	Initial setup, maintenance
Raw Materials	18-30%	Material quality, availability
Labor	<10%	Skilled workforce requirements
Post-Processing	4-13%	Quality control, finishing
Tooling	5%	Equipment adaptability

over 90% of total production costs. In contrast, advanced manufacturing techniques for nanostructured materials demonstrate improved efficiency, with tooling expenses representing merely 5% of total costs [27].

5.1 Manufacturing Cost Breakdown

The production expenses for nanostructured metallic materials encompass multiple cost drivers. Equipment investment represents the most substantial component, accounting for 45-74% of total manufacturing costs. Labor expenses remain relatively modest, constituting less than 10% of overall production costs. Raw material expenses for advanced manufacturing processes exceed traditional methods by up to eight times on a per-weight basis. Nevertheless, these higher material costs find balance through reduced complexity, shorter production times, and significantly lower raw material consumption - often achieving 90% reduction in material usage [28].

Recent advancements in manufacturing processes have addressed previous economic limitations. The EQD process, compatible with existing industrial production lines, circumvents traditional high-cost and low-efficiency challenges. This manufacturing approach enables cost-effective production while maintaining superior material properties, including tensile strength improvements of 60% compared to conventional counterparts (Fig. 5) [29].

Post-processing costs typically range between 4-13% of total production expenses, varying based on specific processes and materials involved. These expenditures remain comparable to traditional manufacturing methods, reflecting similar finishing requirements across both approaches.

Current market analysis suggests defining 'low-cost' materials at production costs below 1 USD/kg, with intermediate and high-cost variants ranging from 3-6 USD/kg and 15-20 USD/kg respectively. Nonetheless, detailed cost analyzes occasionally reveal that presumed 'low-cost' alternatives may prove less economically favorable compared to existing technologies. The economic assessment must consider both immediate production costs alongside long-term benefits. Enhanced material properties often justify higher initial investments through extended service life, reduced maintenance requirements, and improved operational efficiency. Accordingly, lifecycle cost evaluations increasingly demonstrate favorable returns on investment despite higher upfront expenses [30].




Figure 5. High strength metallic wood from nanostructured nickel inverse opal materials

6. Current Applications in Engineering

Nanostructured metallic materials have found their way into critical engineering applications, offering unprecedented combinations of strength, durability, and functionality. These advanced materials now serve essential roles in industries where performance demands continue to rise.

6.1 Aerospace Components

Aerospace applications demand materials that excel under extreme conditions. Boron nitride nanotubes demonstrate remarkable thermal stability, making them ideal for spacecraft thermal protection systems and rocket nozzles. Their electrical insulation properties prove crucial for maintaining component integrity during atmospheric re-entry. Advanced wing designs now incorporate aluminum reinforced with boron nitride, enabling complex geometries while maintaining structural integrity. Graphene-based sensors embedded within aerospace materials provide real-time structural health monitoring, allowing early detection of stress or damage.

6.2 Automotive Parts

The automotive sector has embraced nanostructured metals to enhance vehicle performance and safety. Pure titanium components processed through ECAP exhibit ultimate tensile strength of 1290 MPa alongside 13% tensile elongation. These properties enable the production of lighter, stronger automotive components [31, 32] as in Table 4:

Table 4. Stable Potential Windows

Vehicle Component	Material Properties	Industry Benefits
Body Panels	Nanostructured Steel	Weight reduction
Engine Components	UFG Titanium	Enhanced durability
Brake Systems	Silicon Carbide	Improved wear resistance
Structural Parts	Nanocomposites	Superior crash protection
Protective Coatings	Silver NPs	Antimicrobial properties

Modern family cars incorporate up to 193 different types of steel, each carefully selected for specific applications. Super strong nanometals play a vital role in making vehicles lighter while improving collision protection. Through careful material selection, manufacturers achieve optimal balance between weight reduction and passenger safety.

6.3 Medical Devices

Medical applications of nanostructured metals have shown remarkable progress, primarily in implant technology. High-strength ultrafine-grained pure titanium enables the production of dental implants as thin as 2.0 mm in diameter. These refined structures effectively preserve alveolar bone while maintaining excellent osseointegration [33]. High-purity magnesium demonstrates promising results in orthopedic applications. Clinical trials show exceptional fixation effects when used in ARCO stage II/III patients with femoral head necrosis. The material's controlled degradation rate promotes osteogenic differentiation of stem cells, accelerating fracture healing without requiring secondary removal procedures.

Pure titanium processed through ECAP exhibits self-passivation and enhanced corrosion resistance compared to commercial variants. This advancement enables the development of smaller bone plates with reduced tissue space occupation, maintaining a low-profile design without compromising structural integrity [34, 35]. Recent developments in additive manufacturing have opened new possibilities for pure titanium applications. This technology offers lower production costs alongside improved biocompatibility, presenting a viable alternative to traditional titanium alloys in medical implants. The safety considerations for nanostructured medical devices remain paramount. Regulatory bodies, including the FDA, have highlighted potential toxicity and immunological reactions associated with metal implants. Therefore, ongoing research focuses on understanding long-term biological responses and developing safer alternatives for clinical applications [36, 36].

7. Future Development Areas

7.1 New Processing Methods

Recent breakthroughs in manufacturing techniques herald substantial improvements in nanostructured metallic material production. Dynamic Plastic Deformation stands out as a pioneering approach for synthesizing bulk nanostructured metals. This method offers superior control over material properties alongside enhanced production efficiency. The development of thin-film solid-state interfacial dealloying presents remarkable opportunities for creating metal-metal composites. This technique generates porous metals with interconnected "bicontinuous" structures at scales ranging from tens of nanometers to microns. The process utilizes heat to drive self-organizing mechanisms, enabling metals to mix or de-mix into new structural formations [37, 38]. Electrodeposition emerges as a cost-effective method for creating high entropy alloys. This process, analogous to chrome-plating motorcycle parts, enables the formation of materials that withstand temperatures up to 500°C, markedly higher than pure nickel's limit of 270°C.

7.2 Emerging Applications

The integration of nanostructured metal-organic frameworks into medical applications represents a significant advancement. These frameworks demonstrate exceptional potential in cancer-targeted therapy, primarily through their intrinsically high porosity and ultrahigh surface areas. Their unique properties enable efficient drug molecule loading alongside outstanding stability and real-time intracellular pH sensitivity. The utilization of pulsed laser ablation in organic solvents introduces unprecedented possibilities for gold nanoparticle synthesis. This method requires multiple laser pulses for successful particle generation, yet offers superior control over particle characteristics. Along-

side this advancement, researchers have established correlations between organic phase dielectric constants and nanoparticle extraction capabilities.

Nanoporous gold thin films, prepared through optimized solid-phase reaction methods, demonstrate exceptional catalytic performance. These films exhibit heightened sensitivity and reduced detection limits during amperometric sensing operations, surpassing conventional nanoporous gold materials in analytical applications. The emergence of nanocomposite hydrogels marks another frontier in biomedical applications. These materials combine the advantages of traditional hydrogels with enhanced mechanical properties and functionality. Concurrently, innovative thin films and energy storage devices leverage graphene nanocomposites, establishing new benchmarks in material performance.

Scientists anticipate substantial growth in titanium-based superhydrophobic materials. These innovations utilize novel preparation pathways, potentially revolutionizing surface engineering across multiple industries. The development pathway focuses primarily on achieving consistent superhydrophobicity through controlled nanostructure formation. Research continues to advance manufacturing processes while exploring new applications. Scientists expect significant developments in biomedical applications, energy storage systems, and aerospace materials. These innovations will likely expand the reach and impact of nanostructured metallic materials across industries. The field stands ready for further breakthroughs as researchers develop novel processing methods and uncover new applications. Therefore, understanding these materials becomes essential for engineers and materials scientists working at the forefront of technological advancement.

8. Conclusion

Abstract: This section synthesizes the comprehensive analysis of nanostructured metallic materials, summarizing their superior performance characteristics, manufacturing advancements, real-world applications, and future development potential while highlighting their transformative impact on materials engineering. Nanostructured metallic materials represent a significant advancement in materials science, demonstrating remarkable improvements over traditional alloys. Their enhanced strength-to-weight ratios, superior mechanical properties, and unique characteristics stem from carefully controlled grain sizes and innovative manufacturing processes. Modern manufacturing techniques like mechanical alloying and severe plastic deformation have made these materials commercially viable. Testing data confirms their exceptional performance, with some nanostructured alloys achieving strength levels three times higher than conventional materials while maintaining adequate ductility. Economic analysis shows that despite higher initial costs, nanostructured materials offer substantial long-term value through extended service life and improved performance. Their implementation across aerospace, automotive, and medical sectors demonstrates their practical benefits and reliability.

References

- [1] Alexander S Mcleod, Jingdi Zhang, MQ Gu, Feng Jin, G Zhang, Kirk W Post, XG Zhao, Andrew J Millis, WB Wu, James M Rondinelli, et al. "Multi-messenger nanoprobe of hidden magnetism in a strained manganite". In: *Nature materials* 19.4 (2020), pp. 397–404.
- [2] Arash Ahmadi, Burak Gerislioglu, and Nezih Pala. "Active control over the interplay between the dark and hidden sides of plasmonics using metalodielectric Au–Ge₂Sb₂Te₅ unit cells". In: *The Journal of Physical Chemistry C* 121.36 (2017), pp. 19966–19974.

- [3] Jayaraman Theerthagiri, K Karuppasamy, Govindarajan Durai, Abu Ul Hassan Sarwar Rana, Prabhakarn Arunachalam, Kirubanandam Sangeetha, Parasuraman Kuppasami, and Hyun-Seok Kim. "Recent advances in metal chalcogenides (MX; X= S, Se) nanostructures for electrochemical supercapacitor applications: a brief review". In: *Nanomaterials* 8.4 (2018), p. 256.
- [4] Jimeno Estanislau, Federico Hermogenes, and Bernardo Clemente. "Battery Energy Transformation and Unravelling the Thermodynamics of Energy Storage and Conversion". In: *Fusion of Multidisciplinary Research, An International Journal (FMR)* 2.1 (2021), pp. 122–135.
- [5] Preetha Ganguly, Rwiddhi Sarkhel, Sandipan Bhattacharya, Papita Das, Abhijit Saha, and Avijit Bhowal. "Integral approach of treatment of phenolic wastewater using nano-metal coated graphene oxide in combination with advanced oxidation". In: *Surfaces and Interfaces* 21 (2020), p. 100660.
- [6] Yinmin Wang, Mingwei Chen, Fenghua Zhou, and En Ma. "High tensile ductility in a nanostructured metal". In: *nature* 419.6910 (2002), pp. 912–915.
- [7] Ruo-Yao Zheng, Wu-Rong Jian, Irene J Beyerlein, and Wei-Zhong Han. "Atomic-scale hidden point-defect complexes induce ultrahigh-irradiation hardening in tungsten". In: *Nano Letters* 21.13 (2021), pp. 5798–5804.
- [8] Ishaan Jain, Anjali Reddy, and Nila Rao. "The Widespread Environmental and Health Effects of Microplastics Pollution Worldwide". In: *Fusion of Multidisciplinary Research, An International Journal (FMR)* 2.2 (2021), pp. 224–234.
- [9] Stephen Edward, Hao Zhang, Irwan Setija, Vanessa Verrina, Alessandro Antoncetti, Stefan Witte, and Paul Planken. "Detection of hidden gratings through multilayer nanostructures using light and sound". In: *Physical Review Applied* 14.1 (2020), p. 014015.
- [10] Junyu Zhang, Zhefei Sun, Zewen Kang, Haichen Lin, Haodong Liu, Yang He, Zhiyuan Zeng, and Qiaobao Zhang. "Unveiling the dynamic oxidative etching mechanisms of nanostructured metals/metallic oxides in liquid media through in situ transmission electron microscopy". In: *Advanced Functional Materials* 32.36 (2022), p. 2204976.
- [11] Ramona Kuhn, Isaac Mbir Bryant, Robert Jensch, and Jörg Böllmann. "Applications of environmental nanotechnologies in remediation, wastewater treatment, drinking water treatment, and agriculture". In: *Applied Nano* 3.1 (2022), pp. 54–90.
- [12] Reuven Gordon. "Nanostructured metals for light-based technologies". In: *Nanotechnology* 30.21 (2019), p. 212001.
- [13] Valdemar Johansen, Malthe Rasmussen, and Arne Knudsen. "Dielectric Constants and Their Role in Plasma Simulation". In: *Fusion of Multidisciplinary Research, An International Journal (FMR)* 3.1 (2022), pp. 248–260.
- [14] Min Zha, Hong-Min Zhang, Zhi-Yuan Yu, Xuan-He Zhang, Xiang-Tao Meng, Hui-Yuan Wang, and Qi-Chuan Jiang. "Bimodal microstructure—A feasible strategy for high-strength and ductile metallic materials". In: *Journal of Materials Science & Technology* 34.2 (2018), pp. 257–264.
- [15] Sachiko Ono and Hidetaka Asoh. "A new perspective on pore growth in anodic alumina films". In: *Electrochemistry Communications* 124 (2021), p. 106972.
- [16] Hongyu Jiang, Tongtong Shang, Haijie Xian, Baoan Sun, Qinghua Zhang, Qian Yu, Haiyang Bai, Lin Gu, and Weihua Wang. "Structures and functional properties of amorphous alloys". In: *Small Structures* 2.2 (2021), p. 2000057.
- [17] Ivo Utke, Johann Michler, Robert Winkler, and Harald Plank. "Mechanical properties of 3D nanostructures obtained by focused electron/ion beam-induced deposition: A review". In: *Micromachines* 11.4 (2020), p. 397.
- [18] *Tougher Than Kevlar and Steel: Ultralight Material Withstands Supersonic Microparticle Impacts — scitechdaily.com*. <https://scitechdaily.com/tougher-than-kevlar-and-steel-ultralight-material-withstands-supersonic-microparticle-impacts/>. [Accessed 12-03-2025].
- [19] Meng Ge, Yanzhi Wang, Francesco Carraro, Weibin Liang, Morteza Roostaeinia, Samira Siahrostami, Davide M Proserpio, Christian Doonan, Paolo Falcaro, Haoquan Zheng, et al. "High-Throughput

- Electron Diffraction Reveals a Hidden Novel Metal–Organic Framework for Electrocatalysis”. In: *Angewandte Chemie* 133.20 (2021), pp. 11492–11498.
- [20] Chung Yip, Lokyi Seol, and Xu Zhu Hon. “A Step-by-Step Approach to Partial Differential Equations”. In: *Fusion of Multidisciplinary Research, An International Journal (FMR)* 3.1 (2022), pp. 302–315.
- [21] Muhammad Aamir Iqbal, Maria Malik, Top Khac Le, Nadia Anwar, Sunila Bakhsh, Wajeehah Shahid, Samiah Shahid, Shaheen Irfan, Mohammed Al-Bahrani, Kareem Morsy, et al. “Technological evolution of image sensing designed by nanostructured materials”. In: *ACS Materials Letters* 5.4 (2023), pp. 1027–1060.
- [22] Zhihua Zhu, Philip G Evans, Richard F Haglund Jr, and Jason G Valentine. “Dynamically reconfigurable metadvice employing nanostructured phase-change materials”. In: *Nano letters* 17.8 (2017), pp. 4881–4885.
- [23] Emilia Aleksi and Veera Leevi. “Discovering the Marvels and Intricacies of Physics & Astronomy: A Journey Through Fundamental Principles and Cosmic Phenomena”. In: *Fusion of Multidisciplinary Research, An International Journal (FMR)* 3.2 (2022), pp. 342–353.
- [24] Madeva Nagaral, BK Shivananda, Virupaxi Auradi, and SA Kori. “Development and mechanical-wear characterization of Al₂O₃-nano B₄C composites for aerospace applications”. In: *Strength, Fracture and Complexity* 13.1 (2020), pp. 1–13.
- [25] Byoungsu Ko, Trevon Badloe, Younghwan Yang, Jeonghoon Park, Jaekyung Kim, Heonyeong Jeong, Chunghwan Jung, and Junsuk Rho. “Tunable metasurfaces via the humidity responsive swelling of single-step imprinted polyvinyl alcohol nanostructures”. In: *Nature Communications* 13.1 (2022), p. 6256.
- [26] Linnea Daniel, Sondre Robin, and Matthew Aleksander. “Future Facts: Unveiling Mental Health Issues in the Digital Age”. In: *Fusion of Multidisciplinary Research, An International Journal (FMR)* 3.2 (2022), pp. 354–365.
- [27] Kichul Lee, Incheol Cho, Mingu Kang, Jaeseok Jeong, Minho Choi, Kie Young Woo, Kuk-Jin Yoon, Yong-Hoon Cho, and Inkyu Park. “Ultra-low-power e-nose system based on multi-micro-led-integrated, nanostructured gas sensors and deep learning”. In: *ACS nano* 17.1 (2022), pp. 539–551.
- [28] BV Chaluvvaraju, Asif Afzal, Denis A Vinnik, Abdul Razak Kaladgi, Sagr Alamri, and Vineet Tirth. “Mechanical and corrosion studies of friction stir welded nano Al₂O₃ reinforced Al-Mg matrix composites: RSM-ANN modelling approach”. In: *Symmetry* 13.4 (2021), p. 537.
- [29] James H Pikul, Sezer Özerinç, Burigede Liu, Runyu Zhang, Paul V Braun, Vikram S Deshpande, and William P King. “High strength metallic wood from nanostructured nickel inverse opal materials”. In: *Scientific reports* 9.1 (2019), p. 719.
- [30] Sonali Ajay Beknalkar, Aviraj Mahadev Teli, and Jae Cheol Shin. “Current innovations and future prospects of metal oxide electrospun materials for supercapacitor technology: A review”. In: *Journal of Materials Science & Technology* 166 (2023), pp. 208–233.
- [31] Harshad Kumar Dharamshi Hansraj Bhadeshia and Robert William Kerr Honeycombe. *Steels: microstructure and properties*. Butterworth-Heinemann, 2017.
- [32] Shira Rubin, Daniel Mizrahi, Noam Friedman, Hila Edri, and Tamar Golan. “The World of Advanced Thin Films: Design, Fabrication, and Applications”. In: *Fusion of Multidisciplinary Research, An International Journal (FMR)* 4.1 (2023), pp. 393–406.
- [33] Swati Verma, Ramakrishna Chevvuri, and Hunny Sharma. “Nanotechnology in dentistry: unleashing the hidden gems”. In: *Journal of Indian Society of Periodontology* 22.3 (2018), pp. 196–200.
- [34] Saunak Das, Giulia Nascimbeni, Rodrigo Ortiz De La Morena, Fumitaka Ishiwari, Yoshiaki Shoji, Takanori Fukushima, Manfred Buck, Egbert Zojer, and Michael Zharnikov. “Porous honeycomb self-assembled monolayers: Tripodal adsorption and hidden chirality of carboxylate anchored triptycenes on Ag”. In: *ACS nano* 15.7 (2021), pp. 11168–11179.

- [35] William Yi Wang, Bin Tang, Deye Lin, Chengxiong Zou, Ying Zhang, Shun-Li Shang, Quanmei Guan, Jun Gao, Letian Fan, Hongchao Kou, et al. “A brief review of data-driven ICME for intelligently discovering advanced structural metal materials: Insight into atomic and electronic building blocks”. In: *Journal of Materials Research* 35.8 (2020), pp. 872–889.
- [36] Erfan Maleki and Okan Unal. “Fatigue limit prediction and analysis of nano-structured AISI 304 steel by severe shot peening via ANN”. In: *Engineering with Computers* 37.4 (2021), pp. 2663–2678.
- [37] Yonatan Dubi and Yonatan Sivan. ““Hot” electrons in metallic nanostructures—non-thermal carriers or heating?” In: *Light: Science & Applications* 8.1 (2019), p. 89.
- [38] Li Wang and Justin B Sambur. “Efficient ultrathin liquid junction photovoltaics based on transition metal dichalcogenides”. In: *Nano Letters* 19.5 (2019), pp. 2960–2967.